

Entec Hypro™ PPC-T40 Copolymer Polypropylene, 40% Talc Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Talc Filler

Material Notes:

Information provided by Entec

Order this product through the following link:

http://www.lookpolymers.com/polymer_Entec-Hypro-PPC-T40-Copolymer-Polypropylene-40-Talc-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in ³	ASTM D792
Melt Flow	10.0 g/10 min @Load 2.16 kg, Temperature 230 °C	10.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	25.9 MPa	3760 psi	ASTM D638
Elongation at Break	18.0 %	18.0 %	ASTM D638
Elongation at Yield	6.00 %	6.00 %	ASTM D638
Flexural Strength	46.0 MPa	6670 psi	ASTM D790
Flexural Modulus	2.483 GPa	360.1 ksi	tangent; ASTM D790
Izod Impact, Notched	0.540 J/cm @Thickness 3.17 mm	1.01 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	118 °C	244 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China