

## Entec Hypro™ PPH-CC40 Natural Homopolymer Polypropylene, 40% Calcium Carbonate Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Calcium Carbonate (CaCO<sub>3</sub>) Filler

### Material Notes:

Information provided by Entec

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Entec-Hypro-PPH-CC40-Natural-Homopolymer-Polypropylene-40-Calcium-Carbonate-Filled.php](http://www.lookpolymers.com/polymer_Entec-Hypro-PPH-CC40-Natural-Homopolymer-Polypropylene-40-Calcium-Carbonate-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in <sup>3</sup>	ASTM D792
Melt Flow	10.0 g/10 min @Load 2.16 kg, Temperature 230 °C	10.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	23.5 MPa	3410 psi	ASTM D638
Elongation at Break	25.0 %	25.0 %	ASTM D638
Elongation at Yield	5.00 %	5.00 %	ASTM D638
Flexural Strength	45.0 MPa	6530 psi	ASTM D790
Flexural Modulus	2.207 GPa	320.1 ksi	tangent; ASTM D790
Izod Impact, Notched	0.370 J/cm @Thickness 3.17 mm	0.693 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	113 °C	235 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China