

## Entec Hypro™ PPH-GF20 Natural Homopolymer Polypropylene, 20% Glass Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Glass Fiber Filler

**Material Notes:**

Information provided by Entec

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Entec-Hypro-PPH-GF20-Natural-Homopolymer-Polypropylene-20-Glass-Reinforced.php](http://www.lookpolymers.com/polymer_Entec-Hypro-PPH-GF20-Natural-Homopolymer-Polypropylene-20-Glass-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in <sup>3</sup>	ASTM D792
Melt Flow	10.0 g/10 min @Load 2.16 kg, Temperature 230 °C	10.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	81.0 MPa	11700 psi	ASTM D638
Elongation at Break	4.00 %	4.00 %	ASTM D638
Elongation at Yield	3.00 %	3.00 %	ASTM D638
Flexural Strength	93.0 MPa	13500 psi	ASTM D790
Flexural Modulus	3.517 GPa	510.1 ksi	tangent; ASTM D790
Izod Impact, Notched	0.850 J/cm @Thickness 3.17 mm	1.59 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	149 °C	300 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	132 °C	270 °F	ASTM D648

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

