

## Entec Hyrene® PS-HI 14/2 High Impact Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

**Material Notes:**

Available in North America Features: High Impact ResistanceRoHS Compliant Form: Pellets Information provided by Entec

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Entec-Hyrene-PS-HI-142-High-Impact-Polystyrene.php](http://www.lookpolymers.com/polymer_Entec-Hyrene-PS-HI-142-High-Impact-Polystyrene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Melt Flow	14 g/10 min @Load 5.00 kg, Temperature 200 °C	14 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	20.0 MPa	2900 psi	ASTM D638
Elongation at Break	50 %	50 %	ASTM D638
Flexural Strength	31.0 MPa	4500 psi	ASTM D790
Flexural Modulus	1.77 GPa	256 ksi	ASTM D790
Izod Impact, Notched	1.39 J/cm	2.60 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	77.8 °C	172 °F	Unannealed; ASTM D648
Vicat Softening Point	87.8 °C	190 °F	Rate A (50°C/h), Loading 1 (10 N); ASTM D1525

Compliance Properties	Metric	English	Comments
FDA	Yes	Yes	FDA 21 CFR 177.1640

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China