

## Entec Hyrene® PS-HI 3/2 High Impact Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

**Material Notes:**

Available in North America Features: High Impact ResistanceRoHS Compliant Form: Pellets Information provided by Entec

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Entec-Hyrene-PS-HI-32-High-Impact-Polystyrene.php](http://www.lookpolymers.com/polymer_Entec-Hyrene-PS-HI-32-High-Impact-Polystyrene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Melt Flow	2.9 g/10 min	2.9 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	23.4 MPa	3400 psi	ASTM D638
Elongation at Break	60 %	60 %	ASTM D638
Flexural Strength	38.6 MPa	5600 psi	ASTM D790
Flexural Modulus	1.88 GPa	273 ksi	ASTM D790
Izod Impact, Notched	1.28 J/cm	2.40 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	85.6 °C	186 °F	Unannealed; ASTM D648
Vicat Softening Point	101 °C	213 °F	Rate A (50°C/h), Loading 1 (10 N); ASTM D1525

Compliance Properties	Metric	English	Comments
FDA	Yes	Yes	FDA 21 CFR 177.1640

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China