

## Esstech X-738-0000 Ethoxylated Bis Phenol A Dimethacrylate, C83H144O34

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

### Material Notes:

This form of EBPADMA has 30 units of ethoxylation. It has a high degree of conversion neat and when blended with bisGMA. It also offers high levels of water absorption. Listed on the Toxic Substance Control Act List. CAS # 41637-38-1. Information provided by ESSTECH, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Esstech-X-738-0000-Ethoxylated-Bis-Phenol-A-Dimethacrylate-C83H144O34.php](http://www.lookpolymers.com/polymer_Esstech-X-738-0000-Ethoxylated-Bis-Phenol-A-Dimethacrylate-C83H144O34.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	
Viscosity	600 cP @Temperature 25.0 °C	600 cP @Temperature 77.0 °F	
Molecular Weight	1686 g/mol	1686 g/mol	

Optical Properties	Metric	English	Comments
Refractive Index	1.492	1.492	

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.20 %	<= 0.20 %	

Descriptive Properties	Value	Comments
Acidity (% Methacrylic Acid)	< 0.05	
MeHQ Inhibitor (ppm)	200-250	
Purity (%)	> 87	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China