

## Eurofoam Porocell POR 302/T NBR/PVC Foam

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Acrylonitrile butadiene and polyvinyl chloride foam rubber. Used for thermal insulation and soundproofing, antivibration and waterproofing; different types of gaskets. Information provided by Eurofoam s.r.l.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eurofoam-Porocell-POR-302T-NBRPVC-Foam.php](http://www.lookpolymers.com/polymer_Eurofoam-Porocell-POR-302T-NBRPVC-Foam.php)

Physical Properties	Metric	English	Comments
Density	0.175 - 0.225 g/cc	0.00632 - 0.00813 lb/in <sup>3</sup>	ISO 845-88
Water Absorption	<= 5.0 %	<= 5.0 %	ASTM D 1056

Mechanical Properties	Metric	English	Comments
Hardness, Shore OO	50 - 60	50 - 60	ASTM D 2240
Tensile Strength	1.30 MPa	189 psi	ASTM D 412
Elongation at Break	>= 220 %	>= 220 %	ASTM D 412
Compressive Yield Strength	0.0650 MPa	9.43 psi	TSM 1501 G 2A4
	0.0650 MPa @Strain 25.0 %	9.43 psi @Strain 25.0 %	ASTM 1056/85
Tear Strength	0.420 kN/m	2.40 pli	ASTM D 624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	100 °C	212 °F	ASTM D 3575
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	ASTM D 3575
Flammability, UL94	V-1	V-1	HF1
Shrinkage	<= 5.0 % @Temperature 70.0 °C, Time 605000 sec	<= 5.0 % @Temperature 158 °F, Time 168 hour	Linear; ASTM D 1204

Descriptive Properties	Value	Comments
Cellular Structure	Closed	
Color	Black	

Declaration of Heavy Metal Absence Descriptive Properties	Conform Value	RoHS2002/95/EC Comments
Vulcanization	Peroxide	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China