

## Eurofoam Porocell POR 303/B GR CR-Neoprene/NBR Foam

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Polychloroprene and acrylonitrile butadiene foam rubber. Used for thermal insulation and soundproofing, antivibration and waterproofing; different types of gaskets. Information provided by Eurofoam s.r.l.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eurofoam-Porocell-POR-303B-GR-CR-NeopreneNBR-Foam.php](http://www.lookpolymers.com/polymer_Eurofoam-Porocell-POR-303B-GR-CR-NeopreneNBR-Foam.php)

Physical Properties	Metric	English	Comments
Density	0.125 - 0.175 g/cc	0.00452 - 0.00632 lb/in <sup>3</sup>	ISO 845-88
Water Absorption	<= 5.0 %	<= 5.0 %	ASTM D 1056

Mechanical Properties	Metric	English	Comments
Hardness, Shore OO	45 - 55	45 - 55	ASTM D 2240
Tensile Strength	1.27 MPa	184 psi	ASTM D 412
Elongation at Break	>= 250 %	>= 250 %	ASTM D 412
Compressive Yield Strength	0.0550 MPa @Strain 25.0 %	7.98 psi @Strain 25.0 %	ASTM 1056/85
Tear Strength	0.430 kN/m	2.45 pli	ASTM D 624
Compression Set	20 % @Strain 50.0 %	20 % @Strain 50.0 %	ASTM D 395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	100 °C	212 °F	ASTM D 3575
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	ASTM D 3575
Flammability, UL94	V-1	V-1	HF1
Shrinkage	<= 5.0 % @Temperature 70.0 °C, Time 605000 sec	<= 5.0 % @Temperature 158 °F, Time 168 hour	Linear; ASTM D 1204

Descriptive Properties	Value	Comments
Cellular Structure	Closed	
Color	Grey	

Descriptive Properties	Value	Comments
Declaration of Heavy Metal Absence	Conform	RoHS2002/95/EC
Vulcanization	Peroxide	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China