

## Eurostar Star L PA6 D61 PA6, Injection Molded

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

### Material Notes:

Star L PA6 D61 is a PTFE/Silicone Oil Lubricated, Unreinforced, Polyamide 6 Injection Molding Resin Information provided by Eurostar.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eurostar-Star-L-PA6-D61-PA6-Injection-Molded.php](http://www.lookpolymers.com/polymer_Eurostar-Star-L-PA6-D61-PA6-Injection-Molded.php)

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage, Flow	0.018 - 0.022 cm/cm	0.018 - 0.022 in/in	E2P method
	@Thickness 4.00 mm	@Thickness 0.157 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	62.0 MPa	8990 psi	ISO 527
Elongation at Break	18 %	18 %	ISO 527
Flexural Strength	79.0 MPa	11500 psi	ISO 178
Flexural Modulus	2.10 GPa	305 ksi	ISO 178
Izod Impact, Notched (ISO)	7.00 kJ/m <sup>2</sup>	3.33 ft-lb/in <sup>2</sup>	80x10x4; ISO 180/1A
Izod Impact, Unnotched (ISO)	68.0 kJ/m <sup>2</sup>	32.4 ft-lb/in <sup>2</sup>	80x10x4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	130 °C	266 °F	Flatw 80x10x4, sp=64 mm; ISO 75/Af

Processing Properties	Metric	English	Comments
Zone 1	230 - 240 °C	446 - 464 °F	
Zone 2	235 - 245 °C	455 - 473 °F	
Zone 3	240 - 260 °C	464 - 500 °F	
Melt Temperature	240 - 260 °C	464 - 500 °F	
Mold Temperature	60.0 - 80.0 °C	140 - 176 °F	
Drying Temperature	75.0 - 85.0 °C	167 - 185 °F	
	@Time 14400 - 21600		

Processing Properties	<sup>sec</sup> Metric	@Time 4.00 - 6.00 hour English	Comments
Moisture Content	0.20 %	0.20 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China