

Eurostar Staramide AG5K PA66, 25% Glass Filled, Injection Molded

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled , Nylon 66, Heat Stabilized

Material Notes:

AG5 is a Heat and Hydrolytically Stabilized, 25% Glass Fiber Reinforced Polyamide 66 Injection Molding Resin. Information provided by Polymer Technology & Services, the North American exclusive supplier.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurostar-Staramide-AG5K-PA66-25-Glass-Filled-Injection-Molded.php

Physical Properties	Metric	English	Comments
Density	1.31 g/cc	0.0473 lb/in ³	ISO 1183
Water Absorption at Saturation	6.0 % @Temperature 23.0 °C	6.0 % @Temperature 73.4 °F	ISO 62-1
Linear Mold Shrinkage, Flow	0.0025 - 0.0035 cm/cm	0.0025 - 0.0035 in/in	on Tensile Bar; ISO 294

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	114	114	ISO 2039-2
Tensile Strength at Break	155 MPa	22500 psi	5 mm/min; ISO 527
Elongation at Break	3.0 %	3.0 %	5 mm/min; ISO 527
Tensile Modulus	8.10 GPa	1170 ksi	1 mm/min; ISO 527
Flexural Strength	200 MPa	29000 psi	2 mm/min; ISO 178
Flexural Modulus	7.60 GPa	1100 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	7.00 kJ/m ² @Temperature -30.0 °C	3.33 ft-lb/in ² @Temperature -22.0 °F	80x10x4; ISO 180/1A
	7.00 kJ/m ² @Temperature -40.0 °C	3.33 ft-lb/in ² @Temperature -40.0 °F	80x10x4; ISO 180/1A
	8.00 kJ/m ² @Temperature 23.0 °C	3.81 ft-lb/in ² @Temperature 73.4 °F	80x10x4; ISO 180/1A
Charpy Impact Unnotched	4.50 J/cm ²	21.4 ft-lb/in ²	Edgew 80x10x4; ISO 179/1eU

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	28.0 μm/m-°C @Temperature 23.0 - 60.0 °C	15.6 μin/in-°F @Temperature 73.4 - 140 °F	ISO 11359-2

Thermal Properties	Metric	English	Comments
CTE, linear, Transverse to Flow	@Temperature 23.0 - 60.0 °C	@Temperature 73.4 - 140 °F	ISO 11359-2
Thermal Conductivity	0.330 W/m-K	2.29 BTU-in/hr-ft ² -°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	258 °C	496 °F	Edgew 120x10x4, sp=100 mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	246 °C	475 °F	Edgew 120x10x4, sp=100 mm; ISO 75/Af
Vicat Softening Point	255 °C	491 °F	B/120; ISO 306
UL RTI, Electrical	65.0 °C	149 °F	
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	65.0 °C	149 °F	
	@Thickness 3.00 mm	@Thickness 0.118 in	
UL RTI, Mechanical with Impact	65.0 °C	149 °F	
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	65.0 °C	149 °F	
	@Thickness 3.00 mm	@Thickness 0.118 in	
UL RTI, Mechanical without Impact	65.0 °C	149 °F	
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	65.0 °C	149 °F	
	@Thickness 3.00 mm	@Thickness 0.118 in	
Flammability, UL94	HB	HB	IEC 60695-11-10
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	HB	HB	IEC 60695-11-10
	@Thickness 3.00 mm	@Thickness 0.118 in	
Flame Spread	2.00 mm/min	0.0787 in/min	FMVSS Buring Speed
	@Thickness 3.00 mm	@Thickness 0.118 in	
	6.00 mm/min	0.236 in/min	FMVSS Buring Speed
	@Thickness 2.00 mm	@Thickness 0.0787 in	
Oxygen Index	27 %	27 %	ISO 4589

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	$\geq 1.00\text{e}+16$ ohm-cm Metric	$\geq 1.00\text{e}+16$ ohm-cm English	IEC 60093 Comments
Surface Resistance	$\geq 1.00\text{e}+16$ ohm	$\geq 1.00\text{e}+16$ ohm	ROA; IEC 60093
Dielectric Constant	3.2	3.2	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.4	3.4	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	19.0 kV/mm	483 kV/in	in oil; IEC 60243-1
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.0068	0.0068	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.015	0.015	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	400 V	400 V	M; IEC 60112
	500 V	500 V	IEC 60112

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	260 - 280 °C	500 - 536 °F	Zone 1
Middle Barrel Temperature	270 - 280 °C	518 - 536 °F	Zone 2
Front Barrel Temperature	270 - 290 °C	518 - 554 °F	Zone 3
Melt Temperature	270 - 290 °C	518 - 554 °F	
Mold Temperature	60.0 - 90.0 °C	140 - 194 °F	
Drying Temperature	75.0 - 85.0 °C	167 - 185 °F	
Dry Time	4.00 - 6.00 hour	4.00 - 6.00 hour	
Moisture Content	0.20 %	0.20 %	

Descriptive Properties	Value	Comments
UL f1	f1	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China