

Eurostar Starflam PF0023E PA6, Glass Fiber Filled, Flame Retardant, Injection Molded

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Glass Fiber Filled, Flame Retardant

Material Notes:

Starflam PF0023E is a Mineral Flame Retardant, Halogen Free, Red Phosphorous Free, Glass Fiber Reinforced, Polyamide 6 Injection Molding Resin. Information provided by Eurostar.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurostar-Starflam-PF0023E-PA6-Glass-Fiber-Filled-Flame-Retardant-Injection-Molded.php

Physical Properties	Metric	English	Comments
Density	1.67 g/cc	0.0603 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0030 - 0.0050 cm/cm @Time 86400 sec	0.0030 - 0.0050 in/in @Time 24.0 hour	E2P method

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	95.0 MPa	13800 psi	ISO 527
Tensile Modulus	11.6 GPa	1680 ksi	1 mm/min; ISO 527
Flexural Strength	150 MPa	21800 psi	ISO 178
Flexural Modulus	1.10 GPa	160 ksi	ISO 178
Izod Impact, Notched (ISO)	3.00 kJ/m ²	1.43 ft-lb/in ²	80x10x4; ISO 180/1A
Izod Impact, Unnotched (ISO)	25.0 kJ/m ²	11.9 ft-lb/in ²	80x10x4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	195 °C	383 °F	Flatw 80x10x4, sp=64 mm; ISO 75/Af
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Zone 1	240 - 250 °C	464 - 482 °F	
Zone 2	250 - 260 °C	482 - 500 °F	
Zone 3	250 - 270 °C	482 - 518 °F	
Melt Temperature	250 - 270 °C	482 - 518 °F	

Mold Temperature Processing Properties	50.0 - 90.0 °C Metric	122 - 194 °F English	Comments
Drying Temperature	80.0 °C @Time 14400 sec	176 °F @Time 4.00 hour	
Moisture Content	0.20 %	0.20 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China