

Eurostar Starflam RF0057P PA66/6, 25% Glass Filled, Injection Molded

Category : Polymer , Thermoplastic , Nylon , Nylon 6/66 , Nylon 66/6, 30% Glass Fiber Reinforced

Material Notes:

Starflam RF0057P is a Halogen Free and Red Phosphorous Free, Flame Retardant, Glass Fiber Reinforced, Polyamide 66/6 Injection Molding Resin (also known as RF1005Z270EM) Information provided by Polymer Technology & Services, the North American exclusive supplier.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurostar-Starflam-RF0057P-PA666-25-Glass-Filled-Injection-Molded.php

Physical Properties	Metric	English	Comments
Density	1.39 g/cc	0.0502 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0020 cm/cm	0.0020 in/in	ISO 294

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	130 MPa	18900 psi	5 mm/min; ISO 527
Elongation at Break	2.4 %	2.4 %	5 mm/min; ISO 527
Flexural Strength	195 MPa	28300 psi	2 mm/min; ISO 178
Flexural Modulus	8.10 GPa	1170 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	7.00 kJ/m ²	3.33 ft-lb/in ²	80x10x4; ISO 180/1A
Izod Impact, Unnotched (ISO)	50.0 kJ/m ²	23.8 ft-lb/in ²	80x10x4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Hot Ball Pressure Test	200 °C @Thickness 3.00 mm	392 °F @Thickness 0.118 in	IEC 60695-10-2
Deflection Temperature at 1.8 MPa (264 psi)	215 °C	419 °F	Flatw 80x10x4, sp=64 mm; ISO 75/Af
UL RTI, Electrical	140 °C @Thickness 0.800 mm	284 °F @Thickness 0.0315 in	
	140 °C @Thickness 1.60 mm	284 °F @Thickness 0.0630 in	
	140 °C @Thickness 3.00 mm	284 °F @Thickness 0.118 in	
UL RTI, Mechanical with Impact	105 °C	221 °F	

Thermal Properties	@Thickness 0.800 mm Metric	@Thickness 0.0315 in English	Comments
	105 °C	221 °F	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	105 °C	221 °F	
	@Thickness 3.00 mm	@Thickness 0.118 in	
UL RTI, Mechanical without Impact	140 °C	284 °F	
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	140 °C	284 °F	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	140 °C	284 °F	
	@Thickness 3.00 mm	@Thickness 0.118 in	
Flammability, UL94	V-0	V-0	IEC 60695-11-10
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	V-0	V-0	IEC 60695-11-10
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	IEC 60695-11-10
	@Thickness 3.00 mm	@Thickness 0.118 in	
Glow Wire Test	775 °C	1430 °F	Glow-Wire Ignition; IEC 60695-2-13
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	800 °C	1470 °F	Glow-Wire Ignition; IEC 60695-2-13
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	825 °C	1520 °F	Glow-Wire Ignition; IEC 60695-2-13
	@Thickness 3.00 mm	@Thickness 0.118 in	
	960 °C	1760 °F	Glow-Wire Flammability; IEC 60695-2-12
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	960 °C	1760 °F	Glow-Wire Flammability; IEC 60695-2-12
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	960 °C	1760 °F	Glow-Wire Flammability; IEC 60695-2-12
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	600 V Metric	600 V English	Comments
	@Thickness 3.00 mm	@Thickness 0.118 in	
Hot Wire Ignition, HWI	>= 120 sec	>= 120 sec	PLC 0
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	>= 120 sec	>= 120 sec	PLC 0
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	>= 120 sec	>= 120 sec	PLC 0
	@Thickness 3.00 mm	@Thickness 0.118 in	
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	PLC 0
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	>= 120 arcs	>= 120 arcs	PLC 0
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	>= 120 arcs	>= 120 arcs	PLC 0
	@Thickness 3.00 mm	@Thickness 0.118 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	265 - 275 °C	509 - 527 °F	Zone 1
Middle Barrel Temperature	265 - 275 °C	509 - 527 °F	Zone 2
Front Barrel Temperature	270 - 280 °C	518 - 536 °F	Zone 3
Melt Temperature	270 - 280 °C	518 - 536 °F	
Mold Temperature	60.0 - 100 °C	140 - 212 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	4.00 hour	4.00 hour	
Moisture Content	0.20 %	0.20 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China