

## Eurostar Starpylen MH0200A HDPE, Injection Molding

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Injection Molded

### Material Notes:

Starpylen MH0200A is a High Density Polypropylene Injection Molding Resin. Information provided by Eurostar.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eurostar-Starpylen-MH0200A-HDPE-Injection-Molding.php](http://www.lookpolymers.com/polymer_Eurostar-Starpylen-MH0200A-HDPE-Injection-Molding.php)

Physical Properties	Metric	English	Comments
Density	1.91 g/cc	0.0690 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage, Flow	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	on Tensile Bar; E2P method

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	18.0 MPa	2610 psi	5 mm/min; ISO 527
Elongation at Break	25 %	25 %	5 mm/min; ISO 527
Tensile Modulus	0.450 GPa	65.3 ksi	1 mm/min; ISO 527
Flexural Strength	33.0 MPa	4790 psi	2 mm/min; ISO 178
Flexural Modulus	0.300 GPa	43.5 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	3.00 kJ/m <sup>2</sup>	1.43 ft-lb/in <sup>2</sup>	80x10x4; ISO 180/1A
Izod Impact, Unnotched (ISO)	20.0 kJ/m <sup>2</sup>	9.52 ft-lb/in <sup>2</sup>	80x10x4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	64.0 °C	147 °F	Flatw 80x10x4, sp=64 mm; ISO 75/Af

Processing Properties	Metric	English	Comments
Zone 1	195 - 205 °C	383 - 401 °F	
Zone 2	215 - 225 °C	419 - 437 °F	
Zone 3	225 - 250 °C	437 - 482 °F	
Melt Temperature	225 - 250 °C	437 - 482 °F	
Mold Temperature	30.0 - 50.0 °C	86.0 - 122 °F	
Drying Temperature	70.0 °C	158 °F	
	@Time 10800 sec	@Time 3.00 hour	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**