

## Eurotec® Tecodur® PB70 GB30 NL PBT, 30% glass bead reinforced, natural

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Glass Bead Filled

### Material Notes:

Information provided by Eurotec®

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eurotec-Tecodur-PB70-GB30-NL-PBT-30-glass-bead-reinforced-natural.php](http://www.lookpolymers.com/polymer_Eurotec-Tecodur-PB70-GB30-NL-PBT-30-glass-bead-reinforced-natural.php)

Physical Properties	Metric	English	Comments
Density	1.52 g/cc	0.0549 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.200 % @Temperature 23.0 °C	0.200 % @Temperature 73.4 °F	50% RH; ISO 960
Linear Mold Shrinkage, Flow	0.012 cm/cm	0.012 in/in	Eurotec
Linear Mold Shrinkage, Transverse	0.012 cm/cm	0.012 in/in	Eurotec

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	ISO 527
Elongation at Break	3.5 %	3.5 %	ISO 527
Tensile Modulus	4.00 GPa	580 ksi	ISO 527
Izod Impact, Notched (ISO)	3.00 kJ/m <sup>2</sup> @Temperature -30.0 °C	1.43 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 180/1A
	4.00 kJ/m <sup>2</sup> @Temperature 23.0 °C	1.90 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 180/1A
Izod Impact, Unnotched (ISO)	80.0 kJ/m <sup>2</sup> @Temperature 23.0 °C	38.1 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 180/1U
	190 kJ/m <sup>2</sup> @Temperature -30.0 °C	90.4 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 180/1U

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	[10 K/min], ISO 11357
Deflection Temperature at 0.46 MPa (66 psi)	180 °C	356 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	ISO 75

Thermal Properties	190 °C Metric	374 °F English	Comments
	@Load 5.10 kg	@Load 11.2 lb	
Flammability, UL94	HB	HB	
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Processing Temperature	250 - 270 °C	482 - 518 °F	
Feed Temperature	50.0 - 70.0 °C	122 - 158 °F	Throat
Mold Temperature	60.0 - 100 °C	140 - 212 °F	
Drying Temperature	120 °C	248 °F	
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	
Moisture Content	<= 0.080 %	<= 0.080 %	ISO 960
Hold Pressure	40.0 - 80.0 MPa	5800 - 11600 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Fast	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China