

Eurotec® Tecodur® PB70 GR15 NL XA 20 PBT 15% glass fiber reinforced, UL94 V0

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Excellent stiffness and hardness Good mechanical strength Good creep and fatigue behavior Very good thermal stability Excellent flammability characteristics Good electrical properties High wear resistance and low friction Good dimensional stability Very good chemical resistance Excellent flow and processing properties Low moisture absorption Very good surface finish

APPLICATIONS:
Automotive Electrical/Electronic Business equipment Construction Home appliances

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecodur-PB70-GR15-NL-XA-20-PBT-15-glass-fiber-reinforced-UL94-V0.php

Physical Properties	Metric	English	Comments
Density	1.54 g/cc	0.0556 lb/in ³	ISO 1183
Filler Content	15 %	15 %	ISO 3451
Moisture Absorption at Equilibrium	0.13 %	0.13 %	Humidity Absorption, 50% RH, 23°C; ISO 62
Water Absorption at Saturation	0.35 %	0.35 %	23°C; ISO 62
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	
Linear Mold Shrinkage, Transverse	0.011 cm/cm	0.011 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	95.0 MPa	13800 psi	ISO 527
Elongation at Break	3.0 %	3.0 %	ISO 527
Tensile Modulus	6.50 GPa	943 ksi	ISO 527
Izod Impact, Notched (ISO)	6.00 kJ/m ² @Temperature -30.0 °C	2.86 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1A
	7.00 kJ/m ² @Temperature 23.0 °C	3.33 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1A
Charpy Impact Unnotched	4.50 J/cm ² @Temperature -30.0 °C	21.4 ft-lb/in ² @Temperature -22.0 °F	ISO 179/eU
	5.00 J/cm ² @Temperature 23.0 °C	23.8 ft-lb/in ² @Temperature 73.4 °F	ISO 179/eU
	0.700 J/cm ²	3.33 ft-lb/in ²	

Charpy Impact, Notched Mechanical Properties	Metric @Temperature -30.0 °C	English @Temperature -22.0 °F	ISO 179/eA Comments
	0.800 J/cm ²	3.81 ft-lb/in ²	ISO 179/eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	10 K/min; ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ISO 75-1/2
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ISO 75-1/2
Vicat Softening Point	205 °C	401 °F	50N; ISO 306
Flammability, UL94	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Glow Wire Test	960 °C	1760 °F	plaque; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	IEC 60093
Comparative Tracking Index	225 V	225 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China