

Eurotec® Tecodur® PB70 NL PBT medium viscosity

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Excellent stiffness and hardness
Good mechanical strength
Good creep and fatigue behavior
Very good thermal stability
Excellent flammability characteristics
Good electrical properties
High wear resistance and low friction
Good dimensional stability
Very good chemical resistance
Excellent flow and processing properties
Low moisture absorption
Very good surface finish

APPLICATIONS:
Automotive
Electrical/Electronic
Business equipment
Construction
Home appliances

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecodur-PB70-NL-PBT-medium-viscosity.php

Physical Properties	Metric	English	Comments
Density	1.31 g/cc	0.0473 lb/in ³	ISO 1183
Filler Content	0.00 %	0.00 %	ISO 3451
Moisture Absorption at Equilibrium	0.20 %	0.20 %	Humidity Absorption, 50% RH, 23°C; ISO 62
Water Absorption at Saturation	0.50 %	0.50 %	23°C; ISO 62
Linear Mold Shrinkage	0.016 cm/cm	0.016 in/in	
Linear Mold Shrinkage, Transverse	0.016 cm/cm	0.016 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	55.0 MPa	7980 psi	ISO 527
Elongation at Yield	4.0 %	4.0 %	ISO 527
Tensile Modulus	2.50 GPa	363 ksi	ISO 527
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	6.00 kJ/m ²	2.86 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	NB	NB	ISO 179/eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	NB	NB	ISO 179/eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.400 J/cm ²	1.90 ft-lb/in ²	ISO 179/eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Mechanical Properties	Metric /cm ²	English lb/in ²	Comments
	@Temperature 23.0 °C	@Temperature 73.4 °F	ISO 178/EA

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	10 K/min; ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	160 °C	320 °F	ISO 75-1/2
Deflection Temperature at 1.8 MPa (264 psi)	60.0 °C	140 °F	ISO 75-1/2
Vicat Softening Point	175 °C	347 °F	50N; ISO 306
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Glow Wire Test	750 °C	1380 °F	plaque; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	IEC 60093
Comparative Tracking Index	600 V	600 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China