

Eurotec® Tecolen® CP30 NL MY PPCP, impact modified, heat & UV stabilized, natural

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Impact Modified; Molded/Extruded

Material Notes:

Information provided by Eurotec®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecolen-CP30-NL-MY-PPCP-impact-modified-heat-UV-stabilized-natural.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	15.0 MPa	2180 psi	ISO 527
Elongation at Break	>= 200 %	>= 200 %	ISO 527
Tensile Modulus	0.750 GPa	109 ksi	ISO 527
Izod Impact, Notched (ISO)	60.0 kJ/m ² @Temperature 23.0 °C	28.6 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1A

Thermal Properties	Metric	English	Comments
Melting Point	160 - 165 °C	320 - 329 °F	[10 K/min], ISO 11357
Deflection Temperature at 1.8 MPa (264 psi)	40.0 °C	104 °F	ISO 75
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB @Thickness 0.750 mm	HB @Thickness 0.0295 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Processing Temperature	200 - 240 °C	392 - 464 °F	
Feed Temperature	<= 60.0 °C	<= 140 °F	Throat

Processing Properties	Metric 50.0 °C	English 22 °F	Comments
Hold Pressure	40.0 - 80.0 MPa	5800 - 11600 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Medium - Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China