

Eurotec® Tecomid® NA30 NL RM PA6.6, MoS2 modified, natural

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , MoS2 Filled

Material Notes:

Information provided by Eurotec®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecomid-NA30-NL-RM-PA66-MoS2-modified-natural.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	ISO 1183
Moisture Absorption	2.60 % @Temperature 23.0 °C	2.60 % @Temperature 73.4 °F	50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.014 cm/cm	0.014 in/in	Eurotec
Linear Mold Shrinkage, Transverse	0.014 cm/cm	0.014 in/in	Eurotec

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	85.0 MPa	12300 psi	ISO 527
Tensile Modulus	3.50 GPa	508 ksi	ISO 527
Izod Impact, Notched (ISO)	5.00 kJ/m ² @Temperature -30.0 °C	2.38 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1A
	6.00 kJ/m ² @Temperature 23.0 °C	2.86 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1A
Izod Impact, Unnotched (ISO)	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 180/1U
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	ISO 180/1U

Thermal Properties	Metric	English	Comments
Melting Point	262 °C	504 °F	[10 K/min], ISO 11357
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	ISO 75
Flammability, UL94	HB	HB	

Thermal Properties	@Thickness 0.750 mm Metric	@Thickness 0.0295 in English	Comments
	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Processing Temperature	270 - 290 °C	518 - 554 °F	
Feed Temperature	60.0 - 80.0 °C	140 - 176 °F	Throat
Mold Temperature	50.0 - 90.0 °C	122 - 194 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	
Moisture Content	<= 0.20 %	<= 0.20 %	ISO 960
Hold Pressure	50.0 - 100 MPa	7250 - 14500 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Medium-Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China