

## Eurotec® Tecomid® NA40 GR20 NL PA 6.6 20% glass fiber reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66

### Material Notes:

Excellent stiffness/toughness balance High mechanical strength Very good thermal stability Excellent flammability characteristics Good electrical properties High wear resistance and low friction Very good chemical resistance Good flow and processing properties  
**APPLICATIONS:** Automotive Electrical/Electronic Furniture Construction Home appliances

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eurotec-Tecomid-NA40-GR20-NL-PA-66-20-glass-fiber-reinforced.php](http://www.lookpolymers.com/polymer_Eurotec-Tecomid-NA40-GR20-NL-PA-66-20-glass-fiber-reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.29 g/cc	0.0466 lb/in <sup>3</sup>	ISO 1183
Filler Content	20 %	20 %	ISO 3451
Moisture Absorption at Equilibrium	2.1 %	2.1 %	Humidity Absorption, 50% RH, 23°C; ISO 62
Water Absorption at Saturation	6.5 %	6.5 %	23°C; ISO 62
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	
Linear Mold Shrinkage, Transverse	0.011 cm/cm	0.011 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	155 MPa	22500 psi	ISO 527
Elongation at Break	3.0 %	3.0 %	ISO 527
Tensile Modulus	7.25 GPa	1050 ksi	ISO 527
Flexural Strength	220 MPa	31900 psi	ISO 178
Flexural Modulus	6.75 GPa	979 ksi	ISO 178
Izod Impact, Notched (ISO)	7.00 kJ/m <sup>2</sup>	3.33 ft-lb/in <sup>2</sup>	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	8.00 kJ/m <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	5.00 J/cm <sup>2</sup>	23.8 ft-lb/in <sup>2</sup>	ISO 179/eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	5.50 J/cm <sup>2</sup>	26.2 ft-lb/in <sup>2</sup>	ISO 179/eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Mechanical Properties	0.800 J/cm <sup>2</sup> Metric	3.81 ft-lb/in <sup>2</sup> English	Comments
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	0.900 J/cm <sup>2</sup>	4.28 ft-lb/in <sup>2</sup>	ISO 179/eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	262 °C	504 °F	10 K/min; ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	260 °C	500 °F	ISO 75-1/2
Deflection Temperature at 1.8 MPa (264 psi)	250 °C	482 °F	ISO 75-1/2
Vicat Softening Point	255 °C	491 °F	50N; ISO 306
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Glow Wire Test	650 °C	1200 °F	plaque; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Comparative Tracking Index	500 V	500 V	IEC 60112

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China