

Eurotec® Tecomid® NA40 MR30 NL PA 6.6 30% mineral reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Excellent stiffness/toughness balance High mechanical strength Very good thermal stability Excellent flammability characteristics Good electrical properties High wear resistance and low friction Very good chemical resistance Good flow and processing properties
APPLICATIONS: Automotive Electrical/Electronic Furniture Construction Home appliances

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecomid-NA40-MR30-NL-PA-66-30-mineral-reinforced.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	ISO 1183
Filler Content	30 %	30 %	ISO 3451
Moisture Absorption at Equilibrium	1.9 %	1.9 %	Humidity Absorption, 50% RH, 23°C; ISO 62
Water Absorption at Saturation	6.0 %	6.0 %	23°C; ISO 62
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	
Linear Mold Shrinkage, Transverse	0.010 cm/cm	0.010 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	90.0 MPa	13100 psi	ISO 527
Tensile Modulus	5.50 GPa	798 ksi	ISO 527
Flexural Strength	120 MPa	17400 psi	ISO 178
Flexural Modulus	5.00 GPa	725 ksi	ISO 178
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	6.00 kJ/m ²	2.86 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	8.00 J/cm ²	38.1 ft-lb/in ²	ISO 179/eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	10.0 J/cm ²	47.6 ft-lb/in ²	ISO 179/eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	ISO 179/eA

Mechanical Properties	@Temperature -30.0 °C Metric	@Temperature -22.0 °F English	Comments
	0.700 J/cm ²	3.33 ft-lb/in ²	ISO 179/eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	262 °C	504 °F	10 K/min; ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	210 °C	410 °F	ISO 75-1/2
Deflection Temperature at 1.8 MPa (264 psi)	130 °C	266 °F	ISO 75-1/2
Vicat Softening Point	240 °C	464 °F	50N; ISO 306
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Glow Wire Test	650 °C	1200 °F	plaque; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Comparative Tracking Index	500 V	500 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China