

## Eurotec® Tecomid® NB40 GR20 NL XA 20 PA 6 20% glass fiber reinforced, UL94 V0

Category : Polymer , Thermoplastic , Nylon , Nylon 6

### Material Notes:

Excellent stiffness/toughness balance High mechanical strength Very good thermal stability Excellent flammability characteristics Good electrical properties High wear resistance and low friction Very good chemical resistance Good flow and processing properties  
**APPLICATIONS:** Automotive Electrical/Electronic Furniture Construction Home appliances

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eurotec-Tecomid-NB40-GR20-NL-XA-20-PA-6-20-glass-fiber-reinforced-UL94-V0.php](http://www.lookpolymers.com/polymer_Eurotec-Tecomid-NB40-GR20-NL-XA-20-PA-6-20-glass-fiber-reinforced-UL94-V0.php)

Physical Properties	Metric	English	Comments
Density	1.47 g/cc	0.0531 lb/in <sup>3</sup>	ISO 1183
Filler Content	20 %	20 %	ISO 3451
Moisture Absorption at Equilibrium	2.0 %	2.0 %	Humidity Absorption, 50% RH, 23°C; ISO 62
Water Absorption at Saturation	6.5 %	6.5 %	23°C; ISO 62
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	
Linear Mold Shrinkage, Transverse	0.010 cm/cm	0.010 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	120 MPa	17400 psi	ISO 527
Elongation at Break	3.0 %	3.0 %	ISO 527
Tensile Modulus	8.00 GPa	1160 ksi	ISO 527
Izod Impact, Notched (ISO)	7.00 kJ/m <sup>2</sup>	3.33 ft-lb/in <sup>2</sup>	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	8.00 kJ/m <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	4.00 J/cm <sup>2</sup>	19.0 ft-lb/in <sup>2</sup>	ISO 179/eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	5.00 J/cm <sup>2</sup>	23.8 ft-lb/in <sup>2</sup>	ISO 179/eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.800 J/cm <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	ISO 179/eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Mechanical Properties	Metric /cm <sup>2</sup>	English lb/in <sup>2</sup>	Comments
	@Temperature 23.0 °C	@Temperature 73.4 °F	ISO 178/EA

Thermal Properties	Metric	English	Comments
Melting Point	223 °C	433 °F	10 K/min; ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ISO 75-1/2
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	ISO 75-1/2
Vicat Softening Point	210 °C	410 °F	50N; ISO 306
Flammability, UL94	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Glow Wire Test	960 °C	1760 °F	plaque; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Comparative Tracking Index	250 V	250 V	IEC 60112

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China