

Eurotec® Tecomid® NB40 GR25 NL PA6, 25% glass fiber reinforced, natural

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled

Material Notes:

Information provided by Eurotec®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecomid-NB40-GR25-NL-PA6-25-glass-fiber-reinforced-natural.php

Physical Properties	Metric	English	Comments
Density	1.31 g/cc	0.0473 lb/in ³	ISO 1183
Moisture Absorption	2.20 % @Temperature 23.0 °C	2.20 % @Temperature 73.4 °F	50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0020 cm/cm	0.0020 in/in	Eurotec
Linear Mold Shrinkage, Transverse	0.010 cm/cm	0.010 in/in	Eurotec

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	160 MPa	23200 psi	ISO 527
Elongation at Break	3.5 %	3.5 %	ISO 527
Tensile Modulus	8.50 GPa	1230 ksi	ISO 527
Izod Impact, Notched (ISO)	11.0 kJ/m ² @Temperature -30.0 °C	5.23 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1A
	13.0 kJ/m ² @Temperature 23.0 °C	6.19 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1A
Izod Impact, Unnotched (ISO)	70.0 kJ/m ² @Temperature -30.0 °C	33.3 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1U
	80.0 kJ/m ² @Temperature 23.0 °C	38.1 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1U

Thermal Properties	Metric	English	Comments
Melting Point	223 °C	433 °F	[10 K/min], ISO 11357
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	ISO 75

Thermal Properties	210 °C Metric	410 °F English	Comments
	@Load 5.10 kg	@Load 11.2 lb	
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 0.750 mm	@Thickness 0.0295 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Comparative Tracking Index	500 V	500 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Processing Temperature	250 - 270 °C	482 - 518 °F	
Feed Temperature	60.0 - 80.0 °C	140 - 176 °F	Throat
Mold Temperature	60.0 - 100 °C	140 - 212 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	
Moisture Content	<= 0.20 %	<= 0.20 %	ISO 960
Hold Pressure	50.0 - 100 MPa	7250 - 14500 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China