

## Eurotec® Tecomid® NB50 NL IT PA6, impact modified, super tough, natural, extrusion grade

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Impact Grade

### Material Notes:

Information provided by Eurotec®

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eurotec-Tecomid-NB50-NL-IT-PA6-impact-modified-super-tough-natural-extrusion-grade.php](http://www.lookpolymers.com/polymer_Eurotec-Tecomid-NB50-NL-IT-PA6-impact-modified-super-tough-natural-extrusion-grade.php)

Physical Properties	Metric	English	Comments
Density	1.09 g/cc	0.0394 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	2.30 % @Temperature 23.0 °C	2.30 % @Temperature 73.4 °F	50% RH; ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	45.0 MPa	6530 psi	ISO 527
Elongation at Break	>= 200 %	>= 200 %	ISO 527
Tensile Modulus	0.250 GPa	36.3 ksi	ISO 527
Izod Impact, Notched (ISO)	20.0 kJ/m <sup>2</sup> @Temperature -30.0 °C	9.52 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 180/1A
	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 180/1A
Izod Impact, Unnotched (ISO)	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 180/1U
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	ISO 180/1U

Thermal Properties	Metric	English	Comments
Melting Point	223 °C	433 °F	[10 K/min], ISO 11357
Deflection Temperature at 1.8 MPa (264 psi)	90.0 °C	194 °F	ISO 75
Flammability, UL94	HB @Thickness 0.750 mm	HB @Thickness 0.0295 in	
	HB	HB	

Thermal Properties	@Thickness 1.60 mm Metric	@Thickness 0.0630 in English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Processing Temperature	230 - 250 °C	446 - 482 °F	
Feed Temperature	60.0 - 80.0 °C	140 - 176 °F	Throat
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	
Moisture Content	<= 0.20 %	<= 0.20 %	ISO 960
Hold Pressure	50.0 - 100 MPa	7250 - 14500 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Medium - Fast	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China