

## Eurotec® Tecopet® PT70 GR30 NL100 XA20 PET, 30% glass fiber reinforced, flame retardant - halogen (RoHS compliant), heat stabilized, natural

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), 30% Glass Reinforced

### Material Notes:

Information provided by Eurotec®

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eurotec-Tecopet-PT70-GR30-NL100-XA20-PET-30-glass-fiber-reinforced-flame-retardant-halogen-RoHS-compliant-heat-stabilized-natural.php](http://www.lookpolymers.com/polymer_Eurotec-Tecopet-PT70-GR30-NL100-XA20-PET-30-glass-fiber-reinforced-flame-retardant-halogen-RoHS-compliant-heat-stabilized-natural.php)

Physical Properties	Metric	English	Comments
Density	1.71 g/cc	0.0618 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.200 % @Temperature 23.0 °C	0.200 % @Temperature 73.4 °F	50% RH; ISO 960
Linear Mold Shrinkage, Flow	0.0020 cm/cm	0.0020 in/in	Eurotec
Linear Mold Shrinkage, Transverse	0.0090 cm/cm	0.0090 in/in	Eurotec

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	140 MPa	20300 psi	ISO 527
Elongation at Break	1.5 %	1.5 %	ISO 527
Tensile Modulus	13.0 GPa	1890 ksi	ISO 527
Izod Impact, Notched (ISO)	7.00 kJ/m <sup>2</sup> @Temperature -30.0 °C	3.33 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 180/1A
	8.00 kJ/m <sup>2</sup> @Temperature 23.0 °C	3.81 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 180/1A
Izod Impact, Unnotched (ISO)	35.0 kJ/m <sup>2</sup> @Temperature -30.0 °C	16.7 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 180/1U
	40.0 kJ/m <sup>2</sup> @Temperature 23.0 °C	19.0 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 180/1U

Thermal Properties	Metric	English	Comments
Melting Point	255 °C	491 °F	[10 K/min], ISO 11357
Deflection Temperature at 1.8 MPa (264 psi)	215 °C	419 °F	ISO 75
	V-0	V-0	

Flammability UL 94 Thermal Properties	Metric @Thickness 0.750 mm	English @Thickness 0.0295 in	Comments
	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Glow Wire Test	775 °C	1430 °F	GWIT; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	
	960 °C	1760 °F	GWFI; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	IEC 60093
Comparative Tracking Index	200 V	200 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Processing Temperature	260 - 280 °C	500 - 536 °F	
Feed Temperature	50.0 - 70.0 °C	122 - 158 °F	Throat
Mold Temperature	120 - 140 °C	248 - 284 °F	
Drying Temperature	120 - 140 °C	248 - 284 °F	
Dry Time	4.00 hour	4.00 hour	
Moisture Content	<= 0.080 %	<= 0.080 %	ISO 960
Hold Pressure	60.0 - 100 MPa	8700 - 14500 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Medium - Fast	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China