

## Eurotec® Tecopet® PT74 GR30 BK002 DA PET, 30% glass fiber reinforced, high heat stabilized, black

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), 30% Glass Reinforced

### Material Notes:

Information provided by Eurotec®

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eurotec-Tecopet-PT74-GR30-BK002-DA-PET-30-glass-fiber-reinforced-high-heat-stabilized-black.php](http://www.lookpolymers.com/polymer_Eurotec-Tecopet-PT74-GR30-BK002-DA-PET-30-glass-fiber-reinforced-high-heat-stabilized-black.php)

Physical Properties	Metric	English	Comments
Density	1.57 g/cc	0.0567 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.200 % @Temperature 23.0 °C	0.200 % @Temperature 73.4 °F	50% RH; ISO 960
Linear Mold Shrinkage, Flow	0.0020 cm/cm	0.0020 in/in	Eurotec
Linear Mold Shrinkage, Transverse	0.0090 cm/cm	0.0090 in/in	Eurotec

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	150 MPa	21800 psi	ISO 527
Elongation at Break	2.0 %	2.0 %	ISO 527
Tensile Modulus	11.0 GPa	1600 ksi	ISO 527
Izod Impact, Notched (ISO)	8.00 kJ/m <sup>2</sup> @Temperature -30.0 °C	3.81 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 180/1A
	9.00 kJ/m <sup>2</sup> @Temperature 23.0 °C	4.28 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 180/1A
Izod Impact, Unnotched (ISO)	40.0 kJ/m <sup>2</sup> @Temperature -30.0 °C	19.0 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 180/1U
	45.0 kJ/m <sup>2</sup> @Temperature 23.0 °C	21.4 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 180/1U

Thermal Properties	Metric	English	Comments
Melting Point	250 °C	482 °F	[10 K/min], ISO 11357
Deflection Temperature at 0.46 MPa (66 psi)	235 °C	455 °F	ISO 75
Deflection Temperature at 1.8 MPa	215 °C	419 °F	

Thermal Properties	Metric	English	ISO 75 Comments
Vicat Softening Point	225 °C @Load 5.10 kg	437 °F @Load 11.2 lb	ISO 306
Flammability, UL94	HB @Thickness 0.750 mm	HB @Thickness 0.0295 in	
	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Processing Temperature	270 - 290 °C	518 - 554 °F	
Feed Temperature	50.0 - 70.0 °C	122 - 158 °F	Throat
Mold Temperature	120 - 140 °C	248 - 284 °F	
Drying Temperature	120 - 140 °C	248 - 284 °F	
Dry Time	4.00 hour	4.00 hour	
Moisture Content	<= 0.080 %	<= 0.080 %	ISO 960
Hold Pressure	60.0 - 100 MPa	8700 - 14500 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Fast	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China