

Eurotec® Tecotek® BC40 UF85 NL CE PC/ABS, unfilled, heat & UV stabilized, natural, high heat grade

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Information provided by Eurotec®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecotek-BC40-UF85-NL-CE-PCABS-unfilled-heat-UV-stabilized-natural-high-heat-grade.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	60.0 MPa	8700 psi	ISO 527
Elongation at Break	>= 50 %	>= 50 %	ISO 527
Tensile Modulus	2.25 GPa	326 ksi	ISO 527
Izod Impact, Notched (ISO)	30.0 kJ/m ²	14.3 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	50.0 kJ/m ²	23.8 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Unnotched (ISO)	NB	NB	ISO 180/1U
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	NB	NB	ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	120 °C	248 °F	ISO 75
Vicat Softening Point	130 °C	266 °F	ISO 306
	@Load 5.10 kg	@Load 11.2 lb	
Flammability, UL94	HB	HB	
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Processing Temperature	240 - 260 °C	464 - 500 °F	
Feed Temperature	60.0 - 80.0 °C	140 - 176 °F	Throat
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Drying Temperature	80.0 - 100 °C	176 - 212 °F	
Dry Time	2.00 - 6.00 hour	2.00 - 6.00 hour	
Hold Pressure	50.0 - 100 MPa	7250 - 14500 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Medium - Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China