

ExxonMobil Bicolor® 85 LTSC OPP Film

Category : Polymer , Film , Thermoplastic , Polypropylene (PP) , Polypropylene, Film Grade

Material Notes:

Product Description: Bicolor LTSC is a two-side coated OPP film which is designed for use in high-speed or demanding horizontal, fin seal, packaging applications. The low-temperature seal coating (LTSC) delivers a low seal initiation temperature and wide operating range. LTSC's acrylic surface is excellent for surface printing and provides good aroma barrier. **Availability:** Latin America, North America and South America **Key Features:** Wide sealing range with a low minimum seal temperature (MST) Excellent seal strength and hot tack Robust performances on horizontal flowpack machines Excellent humidity seal retention on LTSC side Good flavor and aroma barrier Outstanding optical properties Ideal support for normal ink system **Features:** Acrylic Coated Flavor & Aroma Barrier Humidity Resistant In Lamination Lap Sealable LTS Coated Very Broad Seal Range **Applications:** Bakery Biscuits/Cookie/Crackers Confectionery, Chocolate Confectionery, Gum Confectionery, Sugar Frozen Food Health and Beauty Care Household and Detergents Tobacco **Uses:** HFF Flexible Packaging Processing **Method:** Inner Web Adhesive Lamination, Solvent Flexographic Printing, Solvent Rotogravure Printing, Surface Print Unsupported and Water-based Flexographic Printing Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Bicolor-85-LTSC-OPP-Film.php

Physical Properties	Metric	English	Comments
Water Vapor Transmission	6.70 g/m ² /day	0.431 g/100 in ² /day	38°C, 90% RH; ExxonMobil Method
Thickness	21.6 microns	0.850 mil	Nominal; ExxonMobil Method
Coating Weight	19.5 g/m ²	12.2 lb/ream	ExxonMobil Method

Mechanical Properties	Metric	English	Comments
Coefficient of Friction	0.24	0.24	ExxonMobil Method
Film Tensile Strength at Break, MD	138 MPa	20000 psi	20 in/min, 2.0 in Jaw Separation; ExxonMobil Method
Film Tensile Strength at Break, TD	234 MPa	34000 psi	20 in/min, 2.0 in Jaw Separation; ExxonMobil Method

Thermal Properties	Metric	English	Comments
Shrinkage, MD	4.5 %	4.5 %	at 275°F; ExxonMobil Method
Shrinkage, TD	4.0 %	4.0 %	at 275°F; ExxonMobil Method

Optical Properties	Metric	English	Comments
Haze	1.9 %	1.9 %	ExxonMobil Method
Gloss	90 %	90 %	45°, Acrylic Surface; ExxonMobil Method

Descriptive Properties	Value	Comments
Crimp Seal MST	160°F	LTSC/LTSC, 200g/in
Crimp Seal Strength	500 g/in	LTSC/LTSC, 260°F, 20psi, 3/4sec
Yield	35500 in ² /lb	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China