

ExxonMobil CM-P Mobilgrease CM Series

Category : Fluid , Lubricant , Lithium Gellant

Material Notes:

Mobilgrease CM Series products are a family of high performance extreme-pressure greases. Mobilgrease CM-P and CM-S are NLGI Grade 2, while Mobilgrease CM-W and CM-L are NLGI Grade 1. All four products are manufactured with a proprietary high-temperature, lithium complex thickener system. They exhibit excellent resistance to softening under severe working, and provide good adhesion and cohesion. An extreme-pressure additive provides exceptional protection against wear and shock loads, while additional additives enhance resistance to high-temperature oxidation and protection against rust. In addition, Mobilgrease CM-P and Mobilgrease CM-L contain 3% molybdenum sulphide for additional wear protection. Other formulation features provide low-temperature dispensing, very good resistance to water wash, and long service in bearings operating at high temperatures. These heavy-duty, severe-service greases have outstanding structural and chemical stability. Mobilgrease CM Series products will not corrode steel or copper-bearing alloys and are compatible with conventional seal materials. Mobilgrease CM greases are recommended for construction and mining sector applications, as well as heavily loaded industrial bearings. Mobilgrease CM-P is recommended for highly loaded plain and antifriction bearings and other applications where the three percent molybdenum disulphide and high-temperature thickener system will provide good performance. Mobilgrease CM-S is recommended for the lubrication of plain and antifriction bearings in contractor and mining vehicles working under severe operating and weather conditions. The recommended application temperature range for Mobilgrease CM-P and CM-S is -20° C to +175° C Mobilgrease CM-L and CM-W are winter-grade products and are recommended for cold-temperature service. The recommended application temperature range for Mobilgrease CM-L and CM-W is -30° C to +175° C. The Mobilgrease CM family of products are highly recommended for heavily loaded applications or environments highly contaminated with water, especially in the contractor / mining sector. Specific examples of such applications include: Heavy-duty trucks especially, hinge and bucket pins; Mining and construction equipment; Highly loaded plain and antifriction industrial bearings

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-CM-P-Mobilgrease-CM-Series.php

| Physical Properties | Metric | English | Comments |
|-------------------------------------|---------|---------|-----------|
| Kinematic Viscosity at 40°C (104°F) | 320 cSt | 320 cSt | ASTM D445 |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|------------|------------|---|
| Four Ball Wear | 0.500 mm | 0.0197 in | ASTM D2266 |
| Penetration | -3.00 | -3.00 | Penetration Consistency Change, mm/10; ASTM D1831 |
| | 280 | 280 | Worked, 25°C, mm/10; ASTM D217 |
| Timken Test | >= 20400 g | >= 45.0 lb | |

| Thermal Properties | Metric | English | Comments |
|--------------------|--------|---------|------------|
| Dropping Point | 260 °C | 500 °F | ASTM D2265 |

| Descriptive Properties | Value | Comments |
|------------------------------------|-----------------|----------|
| Color | grey | |
| Copper Strip Corrosion, ASTM D4048 | 1A | |
| Corrosion Prevention, ASTM D1743 | pass | |
| Soap/Thickener Type | lithium complex | |
| Water Washout, ASTM D1264, wt% | 6 | @ 79°C |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China