

ExxonMobil ENABLE™ EN 33330 Adhesive Resin (discontinued **)

Category : Polymer , Adhesive , Thermoplastic , Ethylene Butyl Acrylate

Material Notes:

Enable EN 33330 is a high flow, 32.5% nBA copolymer suitable for use in hot melt adhesives and sealants. Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-ENABLE-EN-33330-Adhesive-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.922 g/cc	0.0333 lb/in³	ExxonMobil Method
Butyl Acrylate Content	32.5 %	32.5 %	
Melt Flow	330 g/10 min	330 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	56	56	15s; ASTM D2240
Tensile Strength at Break	1.24 MPa	180 psi	ASTM D638
Elongation at Break	270 %	270 %	ASTM D638
Flexural Modulus	0.00724 GPa	1.05 ksi	1% secant; ASTM D790

Thermal Properties	Metric	English	Comments
Melting Point	61.7 °C	143 °F	Peak Melting Temperature; ExxonMobil Method

Descriptive Properties	Value	Comments
Features	Thermal Stabilizer	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China