

ExxonMobil Enable™ 20-10CE Metallocene Polyethylene Resin (Africa & Middle East Grade)

Category : Polymer , Thermoplastic , Polyethylene (PE)

Material Notes:

Product Description: Enable 20-10 resins are metallocene ethylene-hexene copolymers. Enable mPE resins offer an outstanding balance between processing and film properties, including tensile, impact and puncture. Enable 20-10 resins are available with blown film formulations, with or without antiblock. A heavily stabilized formulation for cast film processing is also available. Availability: Africa & Middle East
Additive:Antiblock: 2000 ppmSlip: 500 ppmProcessing Aid: YesThermal Stabilizer: YesApplications: Agricultural FilmBlown FilmCast FilmCast Stretch FilmCollation ShrinkFood packagingForm Fill and Seal PackagingHeavy Duty BagsLamination FilmMultilayer Packaging FilmShrink FilmStand Up PouchesStretch Film Information provided by ExxonMobil

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Enable-20-10CE-Metallocene-Polyethylene-Resin-Africa-Middle-East-Grade.php

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in ³	ExxonMobil method
Melt Flow	1.0 g/10 min @Load 2.16 kg, Temperature 190 °C	1.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238
Antiblock Level	2000 ppm	2000 ppm	
Slip Level	500 ppm	500 ppm	

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	9.65 MPa	1400 psi	ASTM D882
Film Tensile Strength at Yield, TD	10.3 MPa	1500 psi	ASTM D882
Film Elongation at Break, MD	540 %	540 %	ASTM D882
Film Elongation at Break, TD	740 %	740 %	ASTM D882
Puncture Energy	3.39 J	2.50 ft-lb	ExxonMobil Method
Elmendorf Tear Strength MD	110 g	110 g	ASTM D1922
Elmendorf Tear Strength TD	570 g	570 g	ASTM D1922
Dart Drop Test	200 g	0.441 lb	ASTM D1709
Film Tensile Strength at Break, MD	60.7 MPa	8800 psi	ASTM D882
Film Tensile Strength at Break, TD	51.0 MPa	7400 psi	ASTM D882
1% Secant Modulus, MD	200 MPa	29000 psi	ASTM D882

Mechanical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Melting Point	<= 239 °C	<= 462 °F	Peak Melting Point; ExxonMobil method
---------------	-----------	-----------	---------------------------------------

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Haze	7.6 %	7.6 %	ASTM D1003
------	-------	-------	------------

Gloss	65 %	65 %	45°; ASTM D2457
-------	------	------	-----------------

Descriptive Properties	Value	Comments
------------------------	-------	----------

Puncture Force	11 lbf	ExxonMobil Method
----------------	--------	-------------------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China