

## ExxonMobil Enable™ 27-03HH Metallocene Polyethylene Resin

Category : Polymer , Thermoplastic , Polyethylene (PE)

### Material Notes:

**Product Description:** Enable 23-05 resins are metallocene ethylene-hexane copolymers. Enable mPE resins offer an outstanding balance between processing and film properties, including tensile, impact and puncture. Easier processing and excellent properties lead to significant high pressure LDPE replacement in many applications, yet with superior drawdown and enhanced toughness. Enable 23-05 resins are available with and without antiblock  
**Availability:** Latin America, North America and South America  
**Additive:**Antiblock: 2000 ppm  
**Slip:** No Processing Aid: Yes  
**Thermal Stabilizer:** Yes  
**Applications:**Agricultural FilmBlown FilmCollation Shrink Food packagingForm Fill and Seal PackagingHeavy Duty BagsLamination FilmMultilayer Packaging FilmShrink FilmStand Up Pouches  
 Information provided by ExxonMobil

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ExxonMobil-Enable-27-03HH-Metallocene-Polyethylene-Resin.php](http://www.lookpolymers.com/polymer_ExxonMobil-Enable-27-03HH-Metallocene-Polyethylene-Resin.php)

Physical Properties	Metric	English	Comments
Density	0.927 g/cc	0.0335 lb/in <sup>3</sup>	ExxonMobil method
Melt Flow	0.30 g/10 min @Load 2.16 kg, Temperature 190 °C	0.30 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	13.1 MPa	1900 psi	ASTM D882
Film Tensile Strength at Yield, TD	15.2 MPa	2200 psi	ASTM D882
Film Elongation at Break, MD	480 %	480 %	ASTM D882
Film Elongation at Break, TD	750 %	750 %	ASTM D882
Puncture Energy	2.94 J	2.17 ft-lb	ExxonMobil Method
Elmendorf Tear Strength MD	40 g	40 g	ASTM D1922
Elmendorf Tear Strength TD	670 g	670 g	ASTM D1922
Dart Drop Test	140 g	0.309 lb	ASTM D1709A
Film Tensile Strength at Break, MD	64.1 MPa	9300 psi	ASTM D882
Film Tensile Strength at Break, TD	52.4 MPa	7600 psi	ASTM D882
1% Secant Modulus, MD	310 MPa	45000 psi	ASTM D882
1% Secant Modulus, TD	386 MPa	56000 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Melting Point	<= 246 °C	<= 475 °F	Peak Melting Point; ExxonMobil method

Optical Properties	Metric	English	Comments
Haze	12 %	12 %	ASTM D1003
Gloss	42 %	42 %	45°; ASTM D2457

Descriptive Properties	Value	Comments
Puncture Force	11 lbf	ExxonMobil Method

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China