

ExxonMobil Escorene® FL 00111 Film Resin (discontinued **)

Category : Polymer , Film , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Film Grade

Material Notes:

FL 00111 is a copolymer of ethylene and vinyl acetate. Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-FL-00111-Film-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.928 g/cc	0.0335 lb/in ³	ASTM D2839/D1505
Vinyl Acetate Content	7.5 %	7.5 %	ExxonMobil Method
Melt Flow	0.50 g/10 min	0.50 g/10 min	ASTM D1238

Processing Properties	Metric	English	Comments
Processing Temperature	190 - 200 °C	374 - 392 °F	blown film extrusion temp

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China