

ExxonMobil Escorene® HD-7000F HMW-HDPE Blown Film Resin (discontinued **)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Film Grade

Material Notes:

Data provided by the manufacturer, Exxon Chemical. A high molecular weight HDPE blown film resin. Films made from HD-7000F exhibit excellent impact and toughness properties as well as high stiffness. HD-7000F is particularly recommended for films 0.5 mil or greater in thickness. Applications: Retail carry-out sacks; Merchandise bags; Institutional can liners; Consumer trash bags. Data for film properties below based on 0.5 mil film.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-HD-7000F-HMW-HDPE-Blown-Film-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.952 g/cc	0.0344 lb/in ³	Exxon Method
Thickness	12.7 microns	0.500 mil	
Melt Flow	0.045 g/10 min	0.045 g/10 min	Exxon Method (I2). HLMI (I21) is 8 g/10 min.

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	39.0 MPa	5660 psi	ASTM D882
Film Tensile Strength at Yield, TD	33.0 MPa	4790 psi	ASTM D882
Film Elongation at Break, MD	300 %	300 %	ASTM D882
Film Elongation at Break, TD	400 %	400 %	ASTM D882
Secant Modulus, MD	0.965 GPa	140 ksi	ASTM D882
Secant Modulus, TD	1.14 GPa	165 ksi	ASTM D882
Elmendorf Tear Strength, MD	0.591 g/micron	15.0 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	3.15 g/micron	80.0 g/mil	ASTM D1922
Dart Drop	24.6 g/micron	625 g/mil	F50; ASTM D-1709
Film Tensile Strength at Break, MD	93.0 MPa	13500 psi	ASTM D882
Film Tensile Strength at Break, TD	72.0 MPa	10400 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Melting Point	129 °C	264 °F	Exxon Method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China