

ExxonMobil Escorene® LD-312 EVA Film Resin, High Impact (discontinued **)

Category : Polymer , Film , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Film Grade

Material Notes:

Data provided by the manufacturer, Exxon Chemical. A 4.6% vinyl acetate copolymer resin for films with good toughness. This resin's low melt index and comonomer content help produce films which exhibit superior impact strength, good heat sealability and good low temperature properties. Applications: Frozen food packaging; Other food packaging such as heavy duty produce bags, rice bags, poultry bags, etc.; Packaging applications requiring excellent toughness and good heat sealability. Data for film properties below based on 1.25 mil film.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-LD-312-EVA-Film-Resin-High-Impact-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.927 g/cc	0.0335 lb/in ³	Exxon Method
Thickness	31.8 microns	1.25 mil	
Melt Flow	1.0 g/10 min	1.0 g/10 min	Exxon Method

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	8.30 MPa	1200 psi	ASTM D882
Film Tensile Strength at Yield, TD	8.90 MPa	1290 psi	ASTM D882
Film Elongation at Break, MD	150 %	150 %	ASTM D882
Film Elongation at Break, TD	500 %	500 %	ASTM D882
Secant Modulus, MD	0.150 GPa	21.8 ksi	ASTM D882
Secant Modulus, TD	0.190 GPa	27.6 ksi	ASTM D882
Elmendorf Tear Strength MD	350 g	350 g	ASTM D1922
Elmendorf Tear Strength TD	100 g	100 g	ASTM D1922
Elmendorf Tear Strength, MD	11.0 g/micron	280 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	3.15 g/micron	80.0 g/mil	ASTM D1922
Dart Drop	3.15 g/micron	80.0 g/mil	F50; ASTM D1709
Dart Drop Test	100 g	0.221 lb	F50; ASTM D-1709
Film Tensile Strength at Break, MD	28.0 MPa	4060 psi	ASTM D882
Film Tensile Strength at Break, TD	19.0 MPa	2760 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Melting Point	105 °C	221 °F	Exxon Method

Optical Properties	Metric	English	Comments
Haze	6.5 %	6.5 %	ASTM D1003
Gloss	60 %	60 %	45°, ASTM D-2457

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China