

ExxonMobil Escorene® LD-728 High EVA Resin (discontinued **)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Film Grade

Material Notes:

Data provided by the manufacturer, Exxon Chemical. A high vinyl acetate copolymer with a low melting temperature and excellent strength properties and toughness. Applications: Injection molding; Foams.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-LD-728-High-EVA-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in ³	Exxon Method
Environmental Stress Crack Resistance	>= 500 hour	>= 500 hour	F50, Condition A; ASTM D1693
Melt Flow	2.0 g/10 min	2.0 g/10 min	Exxon Method

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	82	82	ASTM D2240
Hardness, Shore D	31	31	ASTM D2240
Tensile Strength, Ultimate	15.0 MPa	2180 psi	ASTM D638
Tensile Strength, Yield	5.00 MPa	725 psi	ASTM D638
Elongation at Break	>= 800 %	>= 800 %	ASTM D638
Flexural Modulus	0.0510 GPa	7.40 ksi	1% Secant, ASTM D790
Tensile Impact Strength	610 kJ/m ²	290 ft-lb/in ²	23°C; ASTM D-1822

Thermal Properties	Metric	English	Comments
Melting Point	85.0 °C	185 °F	Exxon Method
Vicat Softening Point	62.0 °C	144 °F	1000g; ASTM D-1525
Brittleness Temperature	<= -76.0 °C	<= -105 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China