

ExxonMobil Escorene® LD-737 EVA Copolymer for Specialty Applications (discontinued **)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate; Molded/Extruded

Material Notes:

Data provided by the manufacturer, Exxon Chemical.A 19.5% vinyl acetate copolymer.Applications: Compound viscosity modifier; High flow applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-LD-737-EVA-Copolymer-for-Specialty-Applications-nbspdiscontinued-.php

| Physical Properties | Metric | English | Comments |
|-----------------------|--------------|---------------------------|----------------|
| Density | 0.934 g/cc | 0.0337 lb/in ³ | Exxon Method |
| Apparent Bulk Density | 0.545 g/cc | 0.0197 lb/in ³ | ASTM D1895 (B) |
| Melt Flow | 500 g/10 min | 500 g/10 min | Exxon Method |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|----------|---------|-----------|
| Tensile Strength, Ultimate | 3.10 MPa | 450 psi | ASTM D638 |
| Elongation at Break | 240 % | 240 % | ASTM D638 |

| Thermal Properties | Metric | English | Comments |
|-----------------------|---------|---------|---------------------------------|
| Melting Point | 77.0 °C | 171 °F | Exxon Method |
| Vicat Softening Point | 90.0 °C | 194 °F | Softening Point, R&B; ASTM E-28 |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China