

## ExxonMobil Escorene® LL-8555 LLDPE, Rotational Molding Pellets (discontinued \*\*)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Rotational Molding Grade

**Material Notes:**

Data Provided by Exxon Chemical Canada.Characteristics: Fully formulated, UV-4 type protection, High flowUses: Consumer items, Toys, Food storage bins

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ExxonMobil-Escorene-LL-8555-LLDPE-Rotational-Molding-Pellets-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-LL-8555-LLDPE-Rotational-Molding-Pellets-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.935 g/cc	0.0338 lb/in <sup>3</sup>	ASTM D4883
Environmental Stress Crack Resistance	>= 430 hour	>= 430 hour	F-50; 10% Igepal Cond. B; ASTM D1693
Melt Flow	6.8 g/10 min @Load 2.16 kg, Temperature 190 °C	6.8 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	16.9 MPa	2450 psi	ASTM D638
Elongation at Break	415 %	415 %	ASTM D638
Flexural Modulus	0.579 GPa	84.0 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Melting Point	125.5 °C	257.9 °F	Exxon Method
Deflection Temperature at 0.46 MPa (66 psi)	50.0 °C	122 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	38.0 °C	100 °F	ASTM D648

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China