

## ExxonMobil Escorene® MV 02514 EVA Copolymer, Adhesive and Sealant Grade (discontinued \*\*)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Adhesive/Sealant Grade

### Material Notes:

Data provided by the manufacturer, Exxon Chemical.A 14% vinyl acetate copolymerApplications: Hot melt adhesives; Wax blends; Industrial sealants.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ExxonMobil-Escorene-MV-02514-EVA-Copolymer-Adhesive-and-Sealant-Grade-nbspdiscontinued.php](http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-MV-02514-EVA-Copolymer-Adhesive-and-Sealant-Grade-nbspdiscontinued.php)

Physical Properties	Metric	English	Comments
Apparent Bulk Density	0.449 g/cc	0.0162 lb/in <sup>3</sup>	ASTM D1895 (B)
Viscosity	140 cP @Temperature 121 °C	140 cP @Temperature 250 °F	melt viscosity; ASTM D-3236

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	3.60 MPa	522 psi	ASTM D638
Elongation at Yield	70 %	70 %	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	81.0 °C	178 °F	Exxon Method
Vicat Softening Point	88.0 °C	190 °F	Softening Point, R&B; ASTM E-28
Glass Transition Temp, Tg	63.0 °C	145 °F	DSC

Optical Properties	Metric	English	Comments
Refractive Index	1.309	1.309	Exxon Method

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China