

## ExxonMobil Escorene® UL-7505 EVA Copolymer, Adhesive and Sealant Grade (discontinued \*\*)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Adhesive/Sealant Grade

### Material Notes:

Data provided by the manufacturer, Exxon Chemical.A 19.2% vinyl acetate copolymerApplications: Hot melt adhesives; Wax blends; Industrial sealants.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ExxonMobil-Escorene-UL-7505-EVA-Copolymer-Adhesive-and-Sealant-Grade-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-UL-7505-EVA-Copolymer-Adhesive-and-Sealant-Grade-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.947 g/cc	0.0342 lb/in <sup>3</sup>	Exxon Method
Apparent Bulk Density	0.540 g/cc	0.0195 lb/in <sup>3</sup>	ASTM D1895 (B)
Viscosity	300 cP @Temperature 121 °C	300 cP @Temperature 250 °F	melt viscosity; ASTM D-3236
Melt Flow	600 g/10 min	600 g/10 min	Exxon Method

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85	85	ASTM D2240
Tensile Strength, Ultimate	3.40 MPa	493 psi	ASTM D638
Elongation at Break	140 %	140 %	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	78.0 °C	172 °F	Exxon Method
Vicat Softening Point	89.0 °C	192 °F	Softening Point, R&B; ASTM E-28

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China