

ExxonMobil Escorene® UL-7740 EVA Copolymer, Adhesive and Sealant Grade (discontinued **)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Adhesive/Sealant Grade

Material Notes:

Data provided by the manufacturer, Exxon Chemical. A 28% vinyl acetate copolymer. Applications: Hot melt adhesives; Wax blends; Industrial sealants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-UL-7740-EVA-Copolymer-Adhesive-and-Sealant-Grade-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.949 g/cc	0.0343 lb/in ³	Exxon Method
Apparent Bulk Density	0.577 g/cc	0.0208 lb/in ³	ASTM D1895 (B)
Viscosity	1400 cP @Temperature 121 °C	1400 cP @Temperature 250 °F	melt viscosity; ASTM D-3236
Melt Flow	43 g/10 min	43 g/10 min	Exxon Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	4.20 MPa	609 psi	ASTM D638
Elongation at Break	810 %	810 %	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	68.0 °C	154 °F	Exxon Method
Vicat Softening Point	108 °C	226 °F	Softening Point, R&B; ASTM E-28

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China