

ExxonMobil Escorene® UL-7840C EVA Copolymer, Adhesive and Sealant Grade (discontinued **)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Adhesive/Sealant Grade

Material Notes:

Data provided by the manufacturer, Exxon Chemical. A 33% vinyl acetate copolymer. Applications: Hot melt adhesives; Wax blends; Industrial sealants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-UL-7840C-EVA-Copolymer-Adhesive-and-Sealant-Grade-nbspdiscontinued.php

Physical Properties	Metric	English	Comments
Density	0.956 g/cc	0.0345 lb/in ³	Exxon Method
Apparent Bulk Density	0.577 g/cc	0.0208 lb/in ³	ASTM D1895 (B)
Viscosity	1400 cP @Temperature 121 °C	1400 cP @Temperature 250 °F	melt viscosity; ASTM D-3236
Melt Flow	43 g/10 min	43 g/10 min	Exxon Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	3.00 MPa	435 psi	ASTM D638
Elongation at Break	>= 800 %	>= 800 %	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	61.0 °C	142 °F	Exxon Method
Vicat Softening Point	105 °C	221 °F	Softening Point, R&B; ASTM E-28

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China