

ExxonMobil Exceed™ 3518 CB Premium Cast Film Resin

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Blow Molding Grade

Material Notes:

Exceed 3518 resins are hexene copolymer produced using ExxonMobil Chemicals Exxpol® Technology. Films made from 3518 resins have outstanding tensile properties and impact and puncture toughness. These superior properties, along with excellent drawability, make these resins versatile for both monolayer and multilayer cast packaging film. Availability: Latin America, North America and South America Additive: Antiblock: No Slip: No Processing Aid: No Thermal Stabilizer: Yes Applications: Bag in Box Barrier Food Packaging Blown Film Cast Film Cast Stretch Film Diaper Backsheet Food Packaging Form Fill and Seal Packaging Hygiene Film Packaging Films Personal Care Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Exceed-3518-CB-Premium-Cast-Film-Resin.php

Physical Properties	Metric	English	Comments
Density	0.918 g/cc	0.0332 lb/in ³	ExxonMobil Method
Thickness	20.3 microns	0.800 mil	
Melt Flow	3.5 g/10 min	3.5 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	8.27 MPa	1200 psi	at 2% offset; ASTM D882
Film Tensile Strength at Yield, TD	7.58 MPa	1100 psi	at 2% offset; ASTM D882
Film Elongation at Break, MD	510 %	510 %	ASTM D882
Film Elongation at Break, TD	680 %	680 %	ASTM D882
Puncture Energy	4.30 J	3.17 ft-lb	Exxon Mobil Method
Elmendorf Tear Strength MD	190 g	190 g	ASTM D1922
Elmendorf Tear Strength TD	500 g	500 g	ASTM D1922
Elmendorf Tear Strength, MD	9.350 g/micron	237.5 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	24.6 g/micron	625 g/mil	ASTM D1922
Dart Drop	6.89 g/micron	175 g/mil	ASTM D1709
Dart Drop Test	140 g	0.309 lb	ASTM D1709
Film Tensile Strength at Break, MD	73.8 MPa	10700 psi	ASTM D882
Film Tensile Strength at Break, TD	46.7 MPa	6770 psi	ASTM D882
1% Secant Modulus, MD	110 MPa	16000 psi	ASTM D882

Mechanical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
Melting Point	114 °C	237 °F	Peak Melting Temperature; ExxonMobil Method

Optical Properties	Metric	English	Comments
Haze	2.4 %	2.4 %	ASTM D1003
Gloss	86 %	86 %	45°; ASTM D2457

Descriptive Properties	Value	Comments
Features	Thermal Stabilizer	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China