

## ExxonMobil Exterex™ A34 Synthetic Fluid

Category : Fluid , Lubricant

### Material Notes:

**Product Description:** Esterex™ Adipate Esters are API category Group V fluids. These esters have excellent low-temperature properties, high viscosity indices, good lubricating properties and low volatilities. Esterex™ Adipate Esters can be used as sole basestocks or blendstocks with other synthetic fluids in many automotive and industrial lubricant applications. These esters are ideal in high-temperature conditions, such as reciprocating air compressors, where discharge valve cleanliness is required. **Appearance:** Bright & Clear **Availability:** Africa & Middle East, Asia Pacific, Central America, Europe, North America and South America **Information provided by ExxonMobil**

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ExxonMobil-Exterex-A34-Synthetic-Fluid.php](http://www.lookpolymers.com/polymer_ExxonMobil-Exterex-A34-Synthetic-Fluid.php)

Physical Properties	Metric	English	Comments
Density	0.922 g/cc @Temperature 15.6 °C	0.0333 lb/in <sup>3</sup> @Temperature 60.1 °F	ASTM D4052
Viscosity Measurement	137	137	Index; ASTM D2270
Kinematic Viscosity	1970 cSt @Temperature -40.0 °C	1970 cSt @Temperature -40.0 °F	ASTM D445
Kinematic Viscosity at 40°C (104°F)	12 cSt	12 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	3.2 cSt	3.2 cSt	ASTM D445
Evaporation Loss	37 % @Temperature 205 °C, Time 23400 sec	37 % @Temperature 401 °F, Time 6.50 hour	ASTM D972

Thermal Properties	Metric	English	Comments
Pour Point	-60.0 °C	-76.0 °F	ASTM D5950/D97
Flash Point	170 °C	338 °F	PMCC; ASTM D92
	199 °C	390 °F	COC; ASTM D92

Optical Properties	Metric	English	Comments
Refractive Index	1.4487	1.4487	ASTM D1218

Chemical Properties	Metric	English	Comments
Acid Value	<= 0.080	<= 0.080	[mg KOH/g]; ASTM D974 (mod)

Descriptive Properties	Value	Comments
Aniline Point	14.4°F	ASTM D611
Biodegradation	0.785	OECD 301F
Color	<0.5	ASTM D1500
Composition	Water	<1000 ppm, ASTM D6304 (mod)
Density Correction Factor	0.000733 (g/cc)/°C	ASTM D1250
Elastomer Compatibility	-0.024	Fluoroelastomer Elongation Change, ASTM D471
	-0.07	Fluoroelastomer Hardness Change, ASTM D471
	0.086	Fluoroelastomer Volume Change, ASTM D471
	-0.149	Nitrile Tensile Strength Change, ASTM D471
	-0.16	Nitrile Hardness Change, ASTM D471
	0.172	Nitrile Volume Change, ASTM D471
	-0.22	Fluoroelastomer Tensile Strength Change, ASTM D471
	-0.225	Polyacrylate Elongation Change, ASTM D471
	-0.24	Polyacrylate Hardness Change, ASTM D471
	-0.309	Nitrile Elongation Change, ASTM D471
	0.421	Polyacrylate Volume Change, ASTM D471
	-0.45	Polyacrylate Tensile Strength Change, ASTM D471
Fire point	478°F	COC, ASTM D92
Hydrolytic Stability, TAN Change	0.11 mg KOH/g	ASTM D2619
Kauri-Butanol Value	84.5	ASTM D1133
Noack Volatility	0.204	ASTM D5800/DIN 51581
RPVOT	>1210 min	With AO, ASTM D2272

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China