

ExxonMobil HD 9856B Blow Molding Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Blow Molding Grade

Material Notes:

Product Description: HD 9856B is a HDPE blow molding resin designed for high performance packaging applications. Containers made from HD 9856B exhibit a unique combination of stiffness and environmental stress cracking resistance. These properties, coupled with excellent processability on both continuous and intermittent equipment, afford significant lightweighting and/or fast-cycling potential in many applications. HD 9856B does not contain any antistatic. **Availability:** Latin America, North America and South America **Additive:** Thermal Stabilizer: Yes **Antistatic:** No **UV Stabilizer:** No **Applications:** Caps and Closures Compression Moldings Food packaging Household and Industrial chemical containers Pharmaceutical Packaging Thermoformed Parts Thin Gauge Sheet **Information provided by ExxonMobil Chemical**

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-HD-9856B-Blow-Molding-Resin.php

Physical Properties	Metric	English	Comments
Density	0.957 g/cc	0.0346 lb/in ³	ASTM D4883
Environmental Stress Crack Resistance	>= 1000 hour	>= 1000 hour	100% Igepal; ASTM D1693
Melt Flow	0.46 g/10 min @Load 2.16 kg, Temperature 190 °C	0.46 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	24.1 MPa	3500 psi	ASTM D638
Tensile Strength, Yield	30.3 MPa	4400 psi	ASTM D638
Elongation at Break	1100 %	1100 %	ASTM D638
Flexural Modulus	1.45 GPa	210 ksi	1% Secant; ASTM D790
Tensile Impact Strength	252 kJ/m ²	120 ft-lb/in ²	ASTM D1822

Thermal Properties	Metric	English	Comments
Brittleness Temperature	<= -76.1 °C	<= -105 °F	ASTM D746

Descriptive Properties	Value	Comments
Features	Thermal Stabilizer	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China