

## ExxonMobil HDPE HMA 025 High Density Polyethylene Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

**Material Notes:**

Product Description: HMA 025 is a HDPE grade, characterized by excellent dimensional stability, impact strength and very high stiffness.

Availability: Africa &amp; Middle East, Asia Pacific and Europe Additive: Thermal Stabilizer: Yes UV Stabilizer: No Applications: Industrial

Pails Vegetable and Bottle Crates Information provided by ExxonMobil

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ExxonMobil-HDPE-HMA-025-High-Density-Polyethylene-Resin.php](http://www.lookpolymers.com/polymer_ExxonMobil-HDPE-HMA-025-High-Density-Polyethylene-Resin.php)

Physical Properties	Metric	English	Comments
Density	0.964 g/cc	0.0348 lb/in <sup>3</sup>	ASTM D4883
ESCR 10% Igepal®	4.0 hour @Temperature 50.0 °C	4.0 hour @Temperature 122 °F	F50; ASTM D1963
Melt Flow	8.0 g/10 min @Load 2.16 kg, Temperature 190 °C	8.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	26.2 MPa	3800 psi	ISO 527-2/1A/50
Elongation at Break	>= 100 %	>= 100 %	ISO 527-2/1A/50
Elongation at Yield	9.0 %	9.0 %	ISO 527-2/1A/50
Flexural Modulus	1.10 GPa	160 ksi	ISO 178
Izod Impact, Notched (ISO)	6.93 kJ/m <sup>2</sup>	3.30 ft-lb/in <sup>2</sup>	ISO 180/1A

Thermal Properties	Metric	English	Comments
Melting Point	<= 273 °C	<= 523 °F	Peak Melting Point; ExxonMobil method
Deflection Temperature at 0.46 MPa (66 psi)	70.0 °C	158 °F	ISO 75-2/B

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China