

ExxonMobil LD 506.07 Compounding and molding resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Molded

Material Notes:

Product Description: LD 506.07 is a high flow, LDPE homopolymer designed to provide good processability. It is suitable for use in making color concentrates and injection molded articles. **Availability:** Latin America, North America and South America **Additive:** Antiblock: NoSlip: NoThermal Stabilizer: Yes **Applications:** CapsClosuresCompoundingFood Packaging ContainersHouseware ArticlesInjection MoldingMasterbatch Base Resin Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-LD-50607-Compounding-and-molding-resin.php

Physical Properties	Metric	English	Comments
Density	0.921 g/cc	0.0333 lb/in ³	ExxonMobil Method
Melt Flow	33 g/10 min @Load 2.16 kg, Temperature 190 °C	33 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	81 @Time 15.0 sec	81 @Time 0.00417 hour	ASTM D2240
Hardness, Shore D	49	49	15s; ASTM D2240
Tensile Strength at Break	8.27 MPa	1200 psi	ASTM D638
Tensile Strength, Yield	12.4 MPa	1800 psi	ASTM D638
Elongation at Break	130 %	130 %	ASTM D638
Elongation at Yield	20 %	20 %	ASTM D638
Flexural Modulus, 1% Secant	248 MPa	36000 psi	ASTM D790
Dart Drop, Total Energy	16.3 J @Temperature 22.8 °C	12.0 ft-lb @Temperature 73.0 °F	ASTM D3763
	24.4 J @Temperature -20.0 °C	18.0 ft-lb @Temperature -4.00 °F	ASTM D3763

Thermal Properties	Metric	English	Comments
Vicat Softening Point	91.1 °C	196 °F	ASTM D1525

Descriptive Properties	Value	Comments
------------------------	-------	----------

Descriptive Properties

Value al Stabilizer

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China