

ExxonMobil LDPE LD 361BW Low Density Polyethylene Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE

Material Notes:

Product Description: LD 361 series are LEVA LDPE grades, offering good mechanical and sealing properties. Several additive combinations are available according to the required surface properties. **Availability:** Africa & Middle East and Europe **Additive:** Antiblock: NoSlip: No Thermal Stabilizer: Yes **Applications:** Agricultural FilmCo-Extrusion FilmsFoamsForm Fill and Seal PackagingFreezer FilmLamination FilmPoultry BagRice BagsInformation provided by ExxonMobil

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-LDPE-LD-361BW-Low-Density-Polyethylene-Resin.php

Physical Properties	Metric	English	Comments
Density	0.926 g/cc	0.0335 lb/in ³	ExxonMobil method
Melt Flow	0.50 g/10 min	0.50 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	430 %	430 %	ASTM D882
Film Elongation at Break, TD	550 %	550 %	ASTM D882
Elmendorf Tear Strength MD	100 g	100 g	ASTM D1922
Elmendorf Tear Strength TD	130 g	130 g	ASTM D1922
Dart Drop Test	280 g	0.617 lb	ASTM D1709A
Film Tensile Strength at Break, MD	26.9 MPa	3900 psi	ASTM D882
Film Tensile Strength at Break, TD	26.2 MPa	3800 psi	ASTM D882
1% Secant Modulus, MD	159 MPa	23000 psi	ASTM D882
1% Secant Modulus, TD	179 MPa	26000 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Melting Point	<= 219 °C	<= 426 °F	Peak Melting Point; ExxonMobil method

Optical Properties	Metric	English	Comments
Haze	10 %	10 %	ASTM D1003
Gloss	52 %	52 %	45°; ASTM D2457

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China