

ExxonMobil LDPE LD 362HE Low Density Polyethylene Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE

Material Notes:

Product Description: LD 362 series are LEVA LDPE grades, offering good mechanical and sealing properties. Several additive combinations are available according to the required surface properties. **Availability:** Africa & Middle East and Europe **Additive:** Antiblock: 1500 ppm **Slip:** 550 ppm **Thermal Stabilizer:** Yes **Applications:** Agricultural Film Co-Extrusion Films Foams Form Fill and Seal Packaging Freezer Film High Clarity Film Lamination Film Poultry Bag Rice Bags Rubber Bale Wrap **Information provided by ExxonMobil**

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-LDPE-LD-362HE-Low-Density-Polyethylene-Resin.php

Physical Properties	Metric	English	Comments
Density	0.928 g/cc	0.0335 lb/in ³	ExxonMobil method
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238
Antiblock Level	1500 ppm	1500 ppm	
Slip Level	550 ppm	550 ppm	

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	310 %	310 %	ASTM D882
Film Elongation at Break, TD	520 %	520 %	ASTM D882
Elmendorf Tear Strength MD	90 g	90 g	ASTM D1922
Elmendorf Tear Strength TD	90 g	90 g	ASTM D1922
Dart Drop Test	170 g	0.375 lb	ASTM D1709A
Film Tensile Strength at Break, MD	28.3 MPa	4100 psi	ASTM D882
Film Tensile Strength at Break, TD	22.1 MPa	3200 psi	ASTM D882
1% Secant Modulus, MD	159 MPa	23000 psi	ASTM D882
1% Secant Modulus, TD	179 MPa	26000 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Melting Point	<= 219 °C	<= 426 °F	Peak Melting Point; ExxonMobil method

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China