

ExxonMobil LL 6235 Injection Molding Resin (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Injection Molded

Material Notes:

LL 6235 is a narrow molecular weight butene copolymer designed for applications that require easy processability in thin walled parts. This resin offers outstanding toughness and tear resistance in freezer applications for food packaging. Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-LL-6235-Injection-Molding-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.926 g/cc	0.0335 lb/in ³	ASTM D4883
Environmental Stress Crack Resistance	<= 1.0 hour	<= 1.0 hour	Condition B, 10%; ASTM D1693
Melt Flow	35 g/10 min @Load 2.16 kg, Temperature 190 °C	35 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	11.00 MPa	1595 psi	ASTM D638
Elongation at Break	116 %	116 %	ASTM D638
Flexural Modulus	0.250 GPa	36.2 ksi	1% secant; ASTM D790
Tensile Impact Strength	233 kJ/m ² @Temperature -40.0 °C	111 ft-lb/in ² @Temperature -40.0 °F	ASTM D1822

Thermal Properties	Metric	English	Comments
Melting Point	124 °C	255 °F	ASTM D3418
Crystallization Temperature	106 °C	223 °F	ASTM D3418
Vicat Softening Point	92.2 °C	198 °F	ASTM D1525
Brittleness Temperature	>= -70.0 °C	>= -94.0 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China