

ExxonMobil LL 8401.67 Rotational Molding Resin (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Rotational Molding Grade

Material Notes:

LL 8401 is a linear low density hexene copolymer designed to offer excellent ESCR and toughness. This resin is ideally suited for Non-UV applications that require optimum balance of flow processability, stiffness and low temperature toughness. Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-LL-840167-Rotational-Molding-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.938 g/cc	0.0339 lb/in ³	ASTM D4883
Melt Flow	3.3 g/10 min	3.3 g/10 min	ASTM D1238

Thermal Properties	Metric	English	Comments
Melting Point	127 °C	261 °F	ASTM D3418

Descriptive Properties	Value	Comments
Features	non-UV stabilization	
Form	PELLET	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China